

## RESIN GT 50

# CHEMICAL COMPOSITION MODIFIED GLUTARIC DIALDEHYDE

#### **CHARACTERISTICS**

Properties: yellowish liquid

Active substance : 40/45 % pH in solution at 10 % : 3,5 – 5

#### **PROPERTIES**

Low yellowing. Strong tanning action. Good softening effect. Helps the wetting-back in crust leather. Good exhaustion.

#### **APPLICATIONS**

Very effective in the pretanning of all types of leathers, specially for soft ones.

### HOW TO USE

The amount to use in pre-tanning is around 2% based on pelt weight. Feed at a ph below 4,5 and gradually increase it to get a good fixation and a rise in the shrinkage temperature. As retanning agent for soft leathers, use about 3% referred to shaved weight, before neutralization. The addition at ph higher than 5-5,5 increases its astringency, and so a shrunken grain can be obtained by this way.

#### **HEALTH AND SAFETY**

Take the normal caution measures in the handing of chemicals. In case of contact, wash with plenty of water. In case of spill, attention to slippery flor; remove by mechanical means and wash with water.

DATA AND NEWS HAVE INDICATIVE VALUES.